



Properties



mediumtungsten

	AW2110	Typical	Guaranteed
Physical analysis	Fisher size (as delivered) (μm)	1.5	1.3 - 1.7
	Fisher size (lab milled)	1.3	1.1 - 1.5
	Scott density (g/cm^3)	2.3	1.8 - 2.8
	Tap density (g/cm^3)	5.2	4.7 - 5.7
Chemical analysis	W content (O excluded) (wt %)	99.95	> 99.92
	Oxygen content (wt %)	0.2	< 0.30
	Al (ppm)	< 5	< 10
	Ca (ppm)	5	< 10
	Cr (ppm)	25	< 50
	Fe (ppm)	40	< 100
	K (ppm)	< 5	< 10
	Mo (ppm)	10	< 40
	Na (ppm)	< 5	< 10
	Ni (ppm)	10	< 30
	Si (ppm)	10	< 30

eurotungstene® 11/2006 - This is not a legally binding document - V2

Particle size distribution

Laser diffraction

