



Properties



mediumtungsten

	AW2130	Typical	Guaranteed
Physical analysis	Fisher size (as delivered) (μm)	6.0	5.4 - 6.6
	Fisher size (lab milled)	5.3	4.8 - 5.8
	Scott density (g/cm^3)	5.0	4.4 - 5.6
	Tap density (g/cm^3)	7.6	6.9 - 8.3
Chemical analysis	W content (O excluded) (wt %)	99.95	> 99.92
	Oxygen content (wt %)	0.015	< 0.05
	Al (ppm)	< 5	< 10
	Ca (ppm)	5	< 10
	Cr (ppm)	25	< 50
	Fe (ppm)	40	< 100
	K (ppm)	< 5	< 10
	Mo (ppm)	10	< 40
	Na (ppm)	< 5	< 10
	Ni (ppm)	10	< 30
	Si (ppm)	10	< 30

eurotungstene® 03/2008 - This is not a legally binding document - V4

Particle size distribution

Laser diffraction

