

### TECHNICAL DATA SHEET


### CO6101

### Pure Cobalt Powder • COC

#### TYPICAL PHYSICAL AND CHEMICAL DATA

CO6101 powder	
Fisher grain size <i>(µm)</i>	1.6
Scott density (g/cm³)	0.8
Oxygen content (wt %)	0.3
Cobalt content (wt %)	99.8

### % RELATIVE DENSITY




# Minimum sintering temperature 825°C Recommended sintering temperature 850°C Pressure 350kg/cm²

SINTERING CONDITIONS

Holding time

### **HARDNESS**




3 min

## CO6101 Pure Cobalt Powder



### PERFORMANCES - RELATIVE POSITIONING



### SAFETY & MSDS

Material is packed in aluminized plastic bags under inert atmosphere Keep bags tightly closed and in a dry area After opening and to avoid any oxydation, use the desiccant bags placed in the drums for further usage

Review and follow carefully the handling and exposure precautions detailed in the Material Safety Data Sheet (MSDS) or Information Product Sheet (IPS)

For more information, contact toolmaterials@eu.umicore.com