

TECHNICAL DATA SHEET


C07106

Pure Cobalt Powder • COUF

TYPICAL PHYSICAL AND CHEMICAL DATA

C07106 powder		C05106 granulated	
Fisher grain size (μm)	0.9	Scott density (g/cm^3)	2.3
Scott density (g/cm^3)	0.7	Tap density (g/cm^3)	2.6
Oxygen content (wt %)	0.4	Hall flow ($\text{s}/50\text{g}$)	8.0
Cobalt content (wt %)	99.8	Binder (wt %)	2.75
		Granule size (μm)	63 - 450


% RELATIVE DENSITY



SINTERING CONDITIONS

Minimum sintering temperature	775°C
Recommended sintering temperature	800°C
Pressure	350kg/cm ²
Holding time	3 min


HARDNESS



C07106

Pure Cobalt Powder

PERFORMANCES - RELATIVE POSITIONING



SAFETY & MSDS

Material is packed in aluminized plastic bags under inert atmosphere
Keep bags tightly closed and in a dry area
After opening and to avoid any oxydation, use the desiccant bags placed in the drums for further usage

Review and follow carefully the handling and exposure precautions detailed in the Material Safety Data Sheet (MSDS) or Information Product Sheet (IPS)
For more information, contact toolmaterials@eu.umicore.com

GENERAL INFORMATION

Umicore Cobalt and Specialty Materials produces and markets a variety of Cobalt-, Nickel-, or Tungsten-based chemicals and powders for a broad range of industrial applications including hard metals, diamond tools, pigments, catalysis, plating, paint, tires and animal feed.

www.csm.umicore.com
toolmaterials@eu.umicore.com
09/2019 - version 1