

Technical Data Sheet

Date Revision
13/01/2014

Révision
1

Material : Our / Reference

2252UAO

POUDMET Brass powder

25 GT 60/40-325

Brass powder, water atomised, irregular shape

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Sieve analysis ISO 4497 cumulative :						
> 63 µm	%		0,10			IN.V.1007
> 45 µm	%		5,00			IN.V.1007
> 40 µm	%		10,00			IN.V.1007
Apparent density ISO 3923/1 - 2,5 mm	g/cm3	2,60	3,20			IN.V.1010
Chemical						
Chemical analysis :						
Copper (Cu)	%	58,50000	61,50000			IN.V.1024
Zinc (Zn)	%	38,50000	41,50000			IN.V.1142
Others	%		0,20000			IN.V.1142

FDS : 25GT

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale
Poudmet S.A.S.
BP 90319
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z