

Technical Data Sheet

Date Revision
13/01/2014

Révision
2

Material : Our / Reference

2259ZAT

POUDMET Brass powder

25 GT 80/20-80 sp636

Brass powder, water atomised, irregular shape.

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Sieve analysis ISO 4497 residue :						
> 200 µm	%		0,20			IN.V.1007
200 / 160 µm	%		2,00			IN.V.1007
160 / 80 µm	%	13,00	33,00			IN.V.1007
80 / 40 µm	%	24,00	46,00			IN.V.1007
< 40 µm	%	25,00	56,00			IN.V.1007
Apparent density ISO 3923/1 - 2,5 mm	g/cm3	2,70	3,20			IN.V.1010
Flowability ISO 4490 - 2,5 mm	s		30,0			IN.V.1004
Chemical						
Chemical analysis :						
Copper (Cu)	%	79,00000	81,00000			IN.V.1024
Zinc (Zn)	%	19,00000	21,00000			IN.V.1142

FDS : 25GT

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale
Poudmet S.A.S.
BP 90319
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z