

Technical Data Sheet

Date Revision
05/09/2013

Révision
1

Material : Our / Reference

2270UAO

POUDMET Phosphorus copper

25 GO 86/14-200

Copper-phosphorous alloy powder,water atomised,
irregular shape.

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Sieve analysis ISO 4497 cumulative :						
> 100 µm	%		0,10			IN.V.1007
> 80 µm	%		5,00			IN.V.1007
Apparent density ISO 3923/1 - 2,5 mm	g/cm3	2,20	3,00			IN.V.1010
Chemical						
Chemical analysis :						
Phophorus (P)	%	13,00000	14,00000			IN.V.1143
Copper (Cu)	%			86,00		IN.V.1024
Hydrogen Loss ISO 4491/2	%		0,600			IN.V1134

FDS : 25GO

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranted and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvment of production methods.

Adresse postale
Poudmet S.A.S.
BP 90319
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z