

#### TECHNICAL DATA SHEET


## KX1290

### Premixed Pre-Alloyed Powder • Keen®10 + 10% Ni

#### TYPICAL PHYSICAL AND CHEMICAL DATA


KX1290 powder		
Theoretical density (g/cm³)	8.31	
Scott density <i>(g/cm³)</i>	1.9	
Tap density <i>(g/cm³)</i>	3.0	
Oxygen content <i>(wt %)</i>	0.4	

#### % RELATIVE DENSITY



# SINTERING CONDITIONS Minimum sintering temperature 750°C Recommended sintering temperature 800°C Pressure 350kg/cm² Holding time 3 min


#### **HARDNESS**



## KX1290 Premixed Pre-Alloyed Powder



#### PERFORMANCES - RELATIVE POSITIONING



KX1290: ready-to-use premixed powder

Free Cutting

#### **APPLICATIONS**

	☐ Saw blade	Quarry wire	Grinding tool
TOOLS	✓ Core drill	✓ Single wire	☐ Polishing tool
	☐ Gang saw	☐ Multi-wires	☐ Profiling tool
	Limestone	☐ Sandstone	☐ Synthetic stone
MATERIALS	☐ Marble	✓ Concrete	☐ Ceramic
	☐ Granite	□ Asphalt	Glass

Above information is indicative. For detailed recommendation, please contact us.

#### SAFETY & MSDS

Material is packed in aluminized plastic bags under inert atmosphere Keep bags tightly closed and in a dry area

After opening and to avoid any oxydation, use the desiccant bags placed in the drums for further usage

Review and follow carefully the handling and exposure precautions detailed in the Material Safety Data Sheet (MSDS) or Information Product Sheet (IPS)

For more information, contact toolmaterials@eu.umicore.com

tools, pigments, catalysis, plating, paint, tires and animal feed.