

TECHNICAL DATA SHEET


MX1760

Premixed Pre-Alloyed Powder • NEXT®100 + 16% Fe + 20% Br

TYPICAL PHYSICAL AND CHEMICAL DATA

MX1760 powder		
Theoretical density (g/cm³)	8.51	
Scott density (g/cm³)	1.1	
Tap density <i>(g/cm³)</i>	2.4	
Oxygen content <i>(wt %)</i>	0.4	


% RELATIVE DENSITY



SINTERING CONDITIONS Minimum sintering temperature 725°C Recommended sintering temperature 775°C Pressure 350kg/cm²

Holding time

HARDNESS




3 min

MX1760 Premixed Pre-Alloyed Powder



PERFORMANCES - RELATIVE POSITIONING



MX1760 : ready-to-use premixed powder

Free Cutting

APPLICATIONS

	✓ Saw blade	Quarry wire	\square Grinding tool
TOOLS	☐ Core drill	☐ Single wire	☐ Polishing tool
	☐ Gang saw	☐ Multi-wires	☐ Profiling tool
	Limestone	☐ Sandstone	☐ Synthetic stone
MATERIALS	☐ Marble	Concrete	☐ Ceramic
	✓ Granite	☐ Asphalt	Glass

Above information is indicative. For detailed recommendation, please contact us.

SAFETY & MSDS

Material is packed in aluminized plastic bags under inert atmosphere Keep bags tightly closed and in a dry area

After opening and to avoid any oxydation, use the desiccant bags placed in the drums for further usage

Review and follow carefully the handling and exposure precautions detailed in the Material Safety Data Sheet (MSDS) or Information Product Sheet (IPS)

For more information, contact toolmaterials@eu.umicore.com