

TECHNICAL DATA SHEET


MX2480

Premixed Pre-Alloyed Powder • NEXT®200 + 20% Fe

TYPICAL PHYSICAL AND CHEMICAL DATA


MX2480 powder		
Theoretical density (g/cm³)	8.58	
Scott density <i>(g/cm³)</i>	1.0	
Tap density <i>(g/cm³)</i>	2.1	
Oxygen content <i>(wt %)</i>	0.5	

% RELATIVE DENSITY



SINTERING CONDITIONS Minimum sintering temperature 700°C Recommended sintering temperature 750°C Pressure 350kg/cm² Holding time 3 min


HARDNESS



MX2480 Premixed Pre-Alloyed Powder



PERFORMANCES - RELATIVE POSITIONING



MX2480 : ready-to-use premixed powder

Free Cutting

APPLICATIONS

	✓ Saw blade	✓ Quarry wire	\checkmark Grinding tool
TOOLS	✓ Core drill	✓ Single wire	\checkmark Polishing tool
	☐ Gang saw	☐ Multi-wires	\checkmark Profiling tool
	Limestone	☐ Sandstone	☐ Synthetic stone
MATERIALS	✓ Marble	✓ Concrete	☐ Ceramic
		□ Asphalt	Glass

Above information is indicative. For detailed recommendation, please contact us.

SAFETY & MSDS

Material is packed in aluminized plastic bags under inert atmosphere Keep bags tightly closed and in a dry area

After opening and to avoid any oxydation, use the desiccant bags placed in the drums for further usage

Review and follow carefully the handling and exposure precautions detailed in the Material Safety Data Sheet (MSDS) or Information Product Sheet (IPS)

For more information, contact toolmaterials@eu.umicore.com