

TECHNICAL DATA SHEET


MX4590

Base Pre-Alloyed Powder • HCF base

TYPICAL PHYSICAL AND CHEMICAL DATA


MX4590 powder		
Theoretical density (g/cm³)	8.33	
Scott density (g/cm³)	1.0	
Tap density <i>(g/cm³)</i>	2.0	
Oxygen content <i>(wt %)</i>	0.5	

% RELATIVE DENSITY



SINTERING CONDITIONS Minimum sintering temperature 900°C Recommended sintering temperature 950°C Cold Pressure 200 MPa Holding time 60 min


HARDNESS



MX4590 Base Pre-Alloyed Powder



PERFORMANCES - RELATIVE POSITIONING



MX4590: base powder to be mixed with additives to optimize tool performances

Free Cutting

APPLICATIONS

	✓ Saw blade	Quarry wire	✓ Grinding tool
TOOLS	✓ Core drill	✓ Single wire	✓ Polishing tool
	☐ Gang saw	☐ Multi-wires	☐ Profiling tool
	☐ Limestone	✓ Sandstone	☐ Synthetic stone
MATERIALS	☐ Marble	✓ Concrete	☐ Ceramic
	☐ Granite	✓ Asphalt	Glass

Above information is indicative. For detailed recommendation, please contact us.

SAFETY & MSDS

Material is packed in aluminized plastic bags under inert atmosphere Keep bags tightly closed and in a dry area

After opening and to avoid any oxydation, use the desiccant bags placed in the drums for further usage

Review and follow carefully the handling and exposure precautions detailed in the Material Safety Data Sheet (MSDS) or Information Product Sheet (IPS)

For more information, contact toolmaterials@eu.umicore.com

tools, pigments, catalysis, plating, paint, tires and animal feed.