

#### TECHNICAL DATA SHEET


## MX4940

### Premixed Pre-Alloyed Powder • HCF 3

#### TYPICAL PHYSICAL AND CHEMICAL DATA


MX4940 powder		
Theoretical density (g/cm³)	10.85	
Scott density (g/cm³)	1.5	
Tap density (g/cm³)	3.0	
Oxygen content (wt %)	0.5	

#### % RELATIVE DENSITY



# SINTERING CONDITIONS Minimum sintering temperature 950°C Recommended sintering temperature 950°C Cold Pressure 200 MPa Holding time 60 min


#### **HARDNESS**



# MX4940 Premixed Pre-Alloyed Powder



#### PERFORMANCES - RELATIVE POSITIONING



MX4940 : ready-to-use premixed powder

Free Cutting

#### **APPLICATIONS**

	✓ Saw blade	Quarry wire	✓ Grinding tool
TOOLS	✓ Core drill	✓ Single wire	✓ Polishing tool
	☐ Gang saw	☐ Multi-wires	☐ Profiling tool
	☐ Limestone	✓ Sandstone	☐ Synthetic stone
MATERIALS	☐ Marble	✓ Concrete	☐ Ceramic
	☐ Granite	✓ Asphalt	☐ Glass

Above information is indicative. For detailed recommendation, please contact us.

#### SAFETY & MSDS

Material is packed in aluminized plastic bags under inert atmosphere Keep bags tightly closed and in a dry area

After opening and to avoid any oxydation, use the desiccant bags placed in the drums for further usage

Review and follow carefully the handling and exposure precautions detailed in the Material Safety Data Sheet (MSDS) or Information Product Sheet (IPS)

For more information, contact toolmaterials@eu.umicore.com