

Tungsten metal

	AW2110	AW2118	AW2123	AW2130	AW3110	AW3105
Fisher grain size (μm)	1.3 - 1.7	2.1 - 2.9	4.0 - 5.0	5.4 - 6.6	8.0 - 9.0	10.5 - 13.5
Scott density (g/cm^3)	2.3	3.1	4.3	5.0	5.6	7.8
Oxygen content (wt %)	0.2	0.05	0.02	0.015	0.02	0.02

Tungsten carbide

	CW5000	CW5400	CW5522	CW5622	CW5722
Fisher grain size (μm)	0.8 - 1.0	2.2 - 2.8	2.6 - 3.4	3.1 - 3.9	4.5 - 5.5
Scott density (g/cm^3)	2.5	3.7	4.1	4.2	5.0
Oxygen content (wt %)	0.16	0.05	0.03	0.025	0.025

Fused tungsten carbide

	CF1118	CF1122	CF1126	CF1129	CF1133	CF1136
Microns	250 - 450	150 - 250	106 - 150	75 - 106	38 - 75	< 45
Mesh (Tyler)	40 - 60	60 - 100	100 - 140	140 - 200	200 - 400	400
Scott density (g/cm^3)	8.3	8.0	7.7	7.5	7.2	6.2
Oxygen content (wt %)	0.03	0.03	0.03	0.05	0.06	0.1